

## ND Industries SuperGlue Ethyl 309

Category : Polymer , Adhesive , Thermoset

**Material Notes:**

Non-running gel for porous surfaces, general purpose

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_ND-Industries-SuperGlue-Ethyl-309.php](http://www.lookpolymers.com/polymer_ND-Industries-SuperGlue-Ethyl-309.php)

Mechanical Properties	Metric	English	Comments
Shear Strength	20.7 - 24.1 MPa	3000 - 3500 psi	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	82.2 °C	180 °F	
Minimum Service Temperature, Air	-53.9 °C	-65.0 °F	

Processing Properties	Metric	English	Comments
Cure Time	0.500 - 1.17 min	0.00833 - 0.0194 hour	On Steel (Fixture)
	1440 min	24.0 hour	On Steel (Full)

Descriptive Properties	Value	Comments
Color	Clear	
Gap Fill, in.	0.01	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China