

NEU NeuSoft™ 597-60A Industrial Ether TPU / SBC blend

Category : Polymer , Thermoplastic , Polyurethane, TP , Silicone Polyurethane, Ether Based

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_NEU-NeuSoft-597-60A-Industrial-Ether-TPU-SBC-blend.php

Physical Properties	Metric	English	Comments
Density	1.002 g/cc	0.03620 lb/in ³	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	60	60	
Tensile Strength at Break	15.7 MPa	2280 psi	
Tensile Stress	1.68 MPa @Strain 100 %	244 psi @Strain 100 %	
	5.58 MPa @Strain 300 %	810 psi @Strain 300 %	
Elongation at Break	423 %	423 %	
Tear Strength	40.1 kN/m	229 pli	Die C
Compression Set	19.7 %	19.7 %	

Processing Properties	Metric	English	Comments
Moisture Content	<= 0.010 %	<= 0.010 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China