

NEXA® PFX8034 Perfluoroelastomer

Category : Polymer , Thermoset , Fluoropolymer, TS , Thermoset Fluoroelastomer , Rubber or Thermoset Elastomer (TSE)

Material Notes:

NEXA produces sealing elements for extreme and critical applications, particularly where high temperature, wet conditions (steam/water), purity and chemical resistance are important factors to consider. Applications include Aerospace, Automotive, Chemical, Food, Industrial, Pharmaceutical, Semiconductor, Nuclear, and Oil & Gas.

Order this product through the following link:

http://www.lookpolymers.com/polymer_NEXA-PFX8034-Perfluoroelastomer.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	70 - 80	70 - 80	DIN 53505
	@Thickness 6.00 mm	@Thickness 0.236 in	
Tensile Strength	>= 18.0 MPa	>= 2610 psi	DIN 53504
Elongation at Break	>= 160 %	>= 160 %	DIN 53504
100% Modulus	>= 0.00800 GPa	>= 1.16 ksi	DIN 53504
Compression Set	<= 25 %	<= 25 %	DIN 53517
	@Temperature 200 °C, Time 259000 sec	@Temperature 392 °F, Time 72.0 hour	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	260 °C	500 °F	

Descriptive Properties	Value	Comments
Color	Black	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China