

## NIZHNEKAMSKNEFTEKHIM PE 4122N (22401) Linear Low Density Polyethylene

Category : Polymer , Thermoplastic , Polyethylene (PE) , LLDPE

### Material Notes:

Product obtained by gas phase polymerization of ethylene in presence of complex metalorganic catalysts. Information provided by manufacturer

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_NIZHNEKAMSKNEFTEKHIM-PE-4122N-22401-Linear-Low-Density-Polyethylene.php](http://www.lookpolymers.com/polymer_NIZHNEKAMSKNEFTEKHIM-PE-4122N-22401-Linear-Low-Density-Polyethylene.php)

Physical Properties	Metric	English	Comments
Density	0.920 - 0.924 g/cc	0.0332 - 0.0334 lb/in <sup>3</sup>	Base Resin; ASTM D1505
Melt Flow	0.90 - 1.3 g/10 min	0.90 - 1.3 g/10 min	ASTM D1283/L
	@Load 2.16 kg, Temperature 190 °C	@Load 4.76 lb, Temperature 374 °F	
	27 - 39 g/10 min	27 - 39 g/10 min	Flow@21.6kg/Flow@2.16kg ratio < 30; ASTM D1283
	@Load 21.6 kg, Temperature 190 °C	@Load 47.6 lb, Temperature 374 °F	

Mechanical Properties	Metric	English	Comments
Film Tensile Strength at Yield, MD	>= 45.0 MPa	>= 6530 psi	ASTM D882
Film Tensile Strength at Yield, TD	>= 30.0 MPa	>= 4350 psi	ASTM D882
Film Elongation at Break, MD	>= 650 %	>= 650 %	ASTM D882
Film Elongation at Break, TD	>= 700 %	>= 700 %	ASTM D882
Tensile Modulus	>= 0.150 GPa	>= 21.8 ksi	2% sec, MD; ASTM D882
	>= 0.180 GPa	>= 26.1 ksi	2% sec, TD; ASTM D882
Elmendorf Tear Strength, MD	>= 4.72 g/micron	>= 120 g/mil	ASTM D1922
Elmendorf Tear Strength, TD	>= 15.7 g/micron	>= 400 g/mil	ASTM 1922
Dart Drop Test	>= 80.0 g	>= 0.176 lb	ASTM D1709

Descriptive Properties	Value	Comments
Gel Content (pcs./m <sup>2</sup> )	0	> 1mm
	245	(0.2-0.5)mm
	250	> 0.2mm (totally)
	5	(0.5-1.0)mm

Descriptive Properties	Value	Comments
------------------------	-------	----------

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China