

NIZHNEKAMSKNEFTEKHIM PE 4133Q (33403) Medium Density Polyethylene

Category : Polymer , Thermoplastic , Polyethylene (PE) , MDPE

Material Notes:

Product obtained by gas phase polymerization of ethylene in presence of complex metalorganic catalysts. Information provided by manufacturer

Order this product through the following link:

http://www.lookpolymers.com/polymer_NIZHNEKAMSKNEFTEKHIM-PE-4133Q-33403-Medium-Density-Polyethylene.php

Physical Properties	Metric	English	Comments
Density	0.931 - 0.935 g/cc	0.0336 - 0.0338 lb/in ³	Base Resin; ASTM D1505
Melt Flow	2.8 - 3.4 g/10 min	2.8 - 3.4 g/10 min	ASTM D1283/L
	@Load 2.16 kg, Temperature 190 °C	@Load 4.76 lb, Temperature 374 °F	
	84 - 102 g/10 min	84 - 102 g/10 min	Flow@21.6kg/Flow@2.16kg ratio > 30; ASTM D1283
	@Load 21.6 kg, Temperature 190 °C	@Load 47.6 lb, Temperature 374 °F	

Descriptive Properties	Value	Comments
Gel Content (pcs./m ²)	100	

Contact Songhan Plastic Technology Co.,Ltd.Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China