

NIZHNEKAMSKNEFTEKHIM PE 5118P (18602) Linear Low Density Polyethylene

Category : Polymer , Thermoplastic , Polyethylene (PE) , LLDPE

Material Notes:

Product obtained by gas phase polymerization of ethylene in presence of complex metalorganic catalysts. Information provided by manufacturer

Order this product through the following link:

http://www.lookpolymers.com/polymer_NIZHNEKAMSKNEFTEKHIM-PE-5118P-18602-Linear-Low-Density-Polyethylene.php

Physical Properties	Metric	English	Comments
Density	0.916 - 0.920 g/cc	0.0331 - 0.0332 lb/in ³	Base Resin; ASTM D1505
Melt Flow	1.8 - 2.2 g/10 min	1.8 - 2.2 g/10 min	ASTM D1283/L
	@Load 2.16 kg, Temperature 190 °C	@Load 4.76 lb, Temperature 374 °F	
	54 - 66 g/10 min	54 - 66 g/10 min	Flow@21.6kg/Flow@2.16kg ratio < 30; ASTM D1283
	@Load 21.6 kg, Temperature 190 °C	@Load 47.6 lb, Temperature 374 °F	

Mechanical Properties	Metric	English	Comments
Film Tensile Strength at Yield, MD	>= 55.0 MPa	>= 7980 psi	ASTM D882
Film Tensile Strength at Yield, TD	>= 30.0 MPa	>= 4350 psi	ASTM D882
Film Elongation at Break, MD	>= 550 %	>= 550 %	ASTM D882
Film Elongation at Break, TD	>= 900 %	>= 900 %	ASTM D882
Tensile Modulus	>= 0.130 GPa	>= 18.9 ksi	2% sec, MD; ASTM D882
	>= 0.140 GPa	>= 20.3 ksi	2% sec, TD; ASTM D882
Elmendorf Tear Strength, MD	>= 8.66 g/micron	>= 220 g/mil	ASTM D1922
Elmendorf Tear Strength, TD	>= 18.5 g/micron	>= 470 g/mil	ASTM D1922
Dart Drop Test	>= 210 g	>= 0.463 lb	ASTM D1709

Descriptive Properties	Value	Comments
Gel Content (pcs./m ²)	0	> 1mm
	245	(0.2-0.5)mm
	250	> 0.2mm (totally)
	5	(0.5-1.0)mm

Descriptive Properties	Value	Comments
------------------------	-------	----------

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China