

NIZHNEKAMSKNEFTEKHIM PE 6749F (486H6) High Density Polyethylene

Category : Polymer , Thermoplastic , Polyethylene (PE) , HDPE

Material Notes:

Product obtained by gas phase polymerization of ethylene in presence of complex metalorganic catalysts. Information provided by manufacturer

Order this product through the following link:

http://www.lookpolymers.com/polymer_NIZHNEKAMSKNEFTEKHIM-PE-6749F-486H6-High-Density-Polyethylene.php

Physical Properties	Metric	English	Comments
Density	0.946 - 0.950 g/cc	0.0342 - 0.0343 lb/in ³	Base Resin; ASTM D1505
Melt Flow	0.50 - 0.70 g/10 min	0.50 - 0.70 g/10 min	ASTM D1283/L
	@Load 5.00 kg, Temperature 190 °C	@Load 11.0 lb, Temperature 374 °F	
	9.0 - 12.6 g/10 min	9.0 - 12.6 g/10 min	Flow@21.6kg/Flow@5kg ratio > 18; ASTM D1283
	@Load 21.6 kg, Temperature 190 °C	@Load 47.6 lb, Temperature 374 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China