

## NIZHNEKAMSKNEFTEKHIM PE 6752G (526H7) High Density Polyethylene

Category : Polymer , Thermoplastic , Polyethylene (PE) , HDPE

**Material Notes:**

Product obtained by gas phase polymerization of ethylene in presence of complex metalorganic catalysts. Information provided by manufacturer

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_NIZHNEKAMSKNEFTEKHIM-PE-6752G-526H7-High-Density-Polyethylene.php](http://www.lookpolymers.com/polymer_NIZHNEKAMSKNEFTEKHIM-PE-6752G-526H7-High-Density-Polyethylene.php)

Physical Properties	Metric	English	Comments
Density	0.950 - 0.954 g/cc	0.0343 - 0.0345 lb/in <sup>3</sup>	Base Resin; ASTM D1505
Environmental Stress Crack Resistance	200 hour	200 hour	ASTM D1693
Melt Flow	0.60 - 0.80 g/10 min @Load 5.00 kg, Temperature 190 °C	0.60 - 0.80 g/10 min @Load 11.0 lb, Temperature 374 °F	ASTM D1283/L
	10.8 - 14.4 g/10 min @Load 21.6 kg, Temperature 190 °C	10.8 - 14.4 g/10 min @Load 47.6 lb, Temperature 374 °F	Flow@21.6kg/Flow@5kg ratio > 18; ASTM D1283

Mechanical Properties	Metric	English	Comments
Flexural Modulus	>= 1.15 GPa	>= 167 ksi	ASTM D790
Izod Impact, Notched	>= 1.70 J/cm @Temperature 23.0 °C	>= 3.18 ft-lb/in @Temperature 73.4 °F	ASTM D256

### Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China