

## NIZHNEKAMSKNEFTEKHIM PP 4215M (EP1X35F) Propylene and Ethylene Copolymer

Category : Polymer , Thermoplastic , Polyethylene (PE) , Polypropylene (PP)

### Material Notes:

Product obtained by copolymerization of propylene with ethylene in presence of complex metalorganic catalysts. It incorporates increased long-term thermal stability, thermal-oxidative degradation resistance when PP is produced, processed and PP-made articles are exploited, improved properties, contributing to slipping and preventing from film layers sticking. Information provided by manufacturer

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_NIZHNEKAMSKNEFTEKHIM-PP-4215M-EP1X35F-Propylene-and-Ethylene-Copolymer.php](http://www.lookpolymers.com/polymer_NIZHNEKAMSKNEFTEKHIM-PP-4215M-EP1X35F-Propylene-and-Ethylene-Copolymer.php)

Physical Properties	Metric	English	Comments
Melt Flow	7.0 - 10 g/10 min	7.0 - 10 g/10 min	ASTM D1238/L
	@Load 2.16 kg, Temperature 230 °C	@Load 4.76 lb, Temperature 446 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	>= 29.0 MPa	>= 4210 psi	ASTM D638
Elongation at Yield	>= 10 %	>= 10 %	ASTM D638
Flexural Modulus	>= 1.05 GPa	>= 152 ksi	ASTM D790
Izod Impact, Notched	>= 0.350 J/cm	>= 0.656 ft-lb/in	ASTM D256
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Descriptive Properties	Value	Comments
Gel Content (pcs./m <sup>2</sup> )	0	>= 2.5mm
	0	(1.5-2.5)mm
	3	(0.7-1.5)mm
	300	>=0.2mm

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China