

## NIZHNEKAMSKNEFTEKHIM PP 4240G (EP2S29B) Propylene and Ethylene Copolymer

Category : Polymer , Thermoplastic , Polyethylene (PE) , Polypropylene (PP)

### Material Notes:

Product obtained by copolymerization of propylene with ethylene in presence of complex metalorganic catalysts. It incorporates increased long-term thermal stability, thermal-oxidative degradation resistance when PP is produced, processed and PP-made articles are exploited, effective nucleation, and improved optical properties. Information provided by manufacturer

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_NIZHNEKAMSKNEFTEKHIM-PP-4240G-EP2S29B-Propylene-and-Ethylene-Copolymer.php](http://www.lookpolymers.com/polymer_NIZHNEKAMSKNEFTEKHIM-PP-4240G-EP2S29B-Propylene-and-Ethylene-Copolymer.php)

Physical Properties	Metric	English	Comments
Melt Flow	1.5 - 2.0 g/10 min @Load 2.16 kg, Temperature 230 °C	1.5 - 2.0 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238/L

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	>= 27.0 MPa	>= 3920 psi	ASTM D638
Elongation at Yield	>= 11 %	>= 11 %	ASTM D638
Flexural Modulus	>= 0.950 GPa	>= 138 ksi	ASTM D790
Izod Impact, Notched	>= 0.900 J/cm @Temperature 23.0 °C	>= 1.69 ft-lb/in @Temperature 73.4 °F	ASTM D256

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China