

NIZHNEKAMSKNEFTEKHIM PP 8300G (EPYS30RE) Propylene and Ethylene Block Polymer

Category : Polymer , Thermoplastic , Polyethylene (PE) , Polypropylene (PP)

Material Notes:

Product obtained by copolymerization of propylene with ethylene in presence of complex metalorganic catalysts. It incorporates increased long-term thermal stability, thermal-oxidative degradation resistance when PP is produced, processed and PP-made articles are exploited, improved antistatic properties to produce articles. Information provided by manufacturer

Order this product through the following link:

http://www.lookpolymers.com/polymer_NIZHNEKAMSKNEFTEKHIM-PP-8300G-EPYS30RE-Propylene-and-Ethylene-Block-Polymer.php

Physical Properties	Metric	English	Comments
Melt Flow	1.2 - 1.5 g/10 min @Load 2.16 kg, Temperature 230 °C	1.2 - 1.5 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238/L

Mechanical Properties	Metric	English	Comments
Flexural Modulus	>= 1.15 GPa	>= 167 ksi	ASTM D790
Izod Impact, Notched	>= 0.500 J/cm @Temperature -20.0 °C	>= 0.937 ft-lb/in @Temperature -4.00 °F	ASTM D256
	>= 5.00 J/cm @Temperature 23.0 °C	>= 9.37 ft-lb/in @Temperature 73.4 °F	ASTM D256

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China