

## NOVA Chemicals DYLARK® 378 Impact Grade Engineering Resin

Category : Polymer , Thermoplastic , Polystyrene (PS) , Polystyrene, Impact Modified

### Material Notes:

Features: High heat resistance Good chemical resistance High impact strength Excellent flow characteristics Applications: Automotive interior trim applications Automotive consoles Structural Housings Information provided by Nova Chemicals INEOS NOVA began October 1 2007 as an expansion of the 50:50 joint venture between NOVA Chemicals and INEOS to include North American assets.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_NOVA-Chemicals-DYLARK-378-Impact-Grade-Engineering-Resin.php](http://www.lookpolymers.com/polymer_NOVA-Chemicals-DYLARK-378-Impact-Grade-Engineering-Resin.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.06 g/cc	1.06 g/cc	ISO 1183
Linear Mold Shrinkage	0.0060 cm/cm	0.0060 in/in	ISO 2577
Melt Flow	1.0 g/10 min @Load 2.16 kg, Temperature 230 °C	1.0 g/10 min @Load 4.76 lb, Temperature 446 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	30.0 MPa	4350 psi	ISO 527-2
Elongation at Break	12 %	12 %	ISO 527-2
Tensile Modulus	2.30 GPa	334 ksi	ISO 527-2
Flexural Strength	59.0 MPa	8560 psi	ISO 178
Flexural Modulus	2.40 GPa	348 ksi	ISO 178
Izod Impact, Notched (ISO)	7.50 kJ/m <sup>2</sup>	3.57 ft-lb/in <sup>2</sup>	ISO 180/1A
Charpy Impact Unnotched	5.60 J/cm <sup>2</sup>	26.7 ft-lb/in <sup>2</sup>	ISO 179/1eU
Charpy Impact, Notched	0.720 J/cm <sup>2</sup>	3.43 ft-lb/in <sup>2</sup>	ISO 179/1eA

Thermal Properties	Metric	English	Comments
CTE, linear	78.0 µm/m-°C @Temperature 20.0 °C	43.3 µin/in-°F @Temperature 68.0 °F	NOVA Chemicals Laboratory Procedure
Deflection Temperature at 1.8 MPa (264 psi)	99.0 °C @Diameter 4.00 mm	210 °F @Diameter 0.157 in	Unannealed; bar; ISO 75-2

Processing Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Processing Temperature Processing Properties	177 - 260 °C Metric	351 - 500 °F English	Profile temperatures Comments
Melt Temperature	204 - 260 °C	399 - 500 °F	air purge at equilibrium conditions
Mold Temperature	43.0 - 60.0 °C	109 - 140 °F	Core surface temp. at equilibrium
	54.0 - 71.0 °C	129 - 160 °F	Cavity surface temp. at equilibrium
Back Pressure	0.345 - 0.689 MPa	50.0 - 100 psi	Typically 50 psi
Screw Speed	40 - 80 rpm	40 - 80 rpm	

Descriptive Properties	Value	Comments
Injection Speed	medium-fast	Typically fast

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China