

## NOVA Chemicals Dytherm® 370R Expandable Polystyrene

Category : Polymer , Thermoplastic , Polystyrene (PS) , Expanded Polystyrene (EPS)

**Material Notes:**

This is a special grade consisting of spherical beads of a blend of polystyrene-polyphenylene ether containing pentane as expansion agent, typically used for medium density foam with improved thermal resistance. Applications: This grade is used for medium density foam with wall-thickness generally greater than or equal to 10 mm and with improved thermal resistance. Typical applications include hot-water insulation and automotive parts (interior and exterior). Processing of DYTHERM beads on pressurized batch pre-expander is recommended. It can be process on a continuous pre-expander when higher densities are acceptable. This grade should not be used for food contact applications. Information provided by NOVA Chemicals.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_NOVA-Chemicals-Dytherm-370R-Expandable-Polystyrene.php](http://www.lookpolymers.com/polymer_NOVA-Chemicals-Dytherm-370R-Expandable-Polystyrene.php)

Physical Properties	Metric	English	Comments
Bulk Density	0.620 g/cc	0.0224 lb/in <sup>3</sup>	
Density	>= 0.0350 g/cc	>= 0.00126 lb/in <sup>3</sup>	Minimum achievable; Single stage pre-expansion in continuous expander at atmospheric pressure
	0.0350 - 0.100 g/cc	0.00126 - 0.00361 lb/in <sup>3</sup>	Normal molded density assuming cost optimized selection of processing conditions.
Bead Size	0.300 - 0.700 mm	0.0118 - 0.0276 in	Breda Laboratory Analytical Methods 90.30
	0.400 - 0.700 mm	0.0157 - 0.0276 in	

Chemical Properties	Metric	English	Comments
Styrene Content	<= 0.10 %	<= 0.10 %	Residual Styrene Monomer Content per Breda Laboratory Analytical Methods 90.16
Blowing Agent Content	>= 5.8 %	>= 5.8 %	Breda Laboratory Analytical Methods 90.18

### Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China