

## NOVA Chemicals Novapol® LC-0717-A LDPE Extrusion Resin

Category : Polymer , Thermoplastic , Polyethylene (PE) , LDPE , Low Density Polyethylene (LDPE), Extrusion Grade

### Material Notes:

High speeds, Low coating weights, Excellent adhesion, Excellent drawdown, Excellent sealability  
 Applications: Sugar pouch stock; Popsicle wrap, Multi-wall bags, High speed/low coating weight paper coating, Flexible and snack food packaging, Coating of non-porous substrates  
 Additives: Base resin  
 Information provided by NOVA Chemicals.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_NOVA-Chemicals-Novapol-LC-0717-A-LDPE-Extrusion-Resin.php](http://www.lookpolymers.com/polymer_NOVA-Chemicals-Novapol-LC-0717-A-LDPE-Extrusion-Resin.php)

Physical Properties	Metric	English	Comments
Density	0.917 g/cc	0.0331 lb/in <sup>3</sup>	ASTM D792
Water Vapor Transmission	18.0 g/m <sup>2</sup> /day	1.16 g/100 in <sup>2</sup> /day	WVT is done at 100°F, 90% relative humidity on 30 lb Kraft paper samples with LDPE coating weight of 15 lb/ream.; ASTM E96
Melt Flow	7.0 g/10 min @Load 2.16 kg, Temperature 190 °C	7.0 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238
Neck In	5.50 cm	2.17 in	at 1000 ft/min; Neck-in reported is the total of both sides; NOVA Chemicals test method
Drawdown	>= 9.10 m/s	>= 1790 ft/min	NOVA Chemical test method
Coating Weight	>= 6.40 g/m <sup>2</sup>	>= 4.00 lb/ream	TAPPI test method; ASTM D539

Mechanical Properties	Metric	English	Comments
Hot Tack Strength	225 g/25 mm	225 g/in	Tests done on samples with a coating weight of 12 lb/ream, prepared under the following extrusion coating conditions: Output Rate: 3 lb/hr/in, Melt Temp: 600°F, Die Width: 12 in, Substrate: 40 lb Kraft paper. Mfr reports 450 g per 50 mm (2 in).
Heat Seal Strength	1400 g/25 mm	3.09 lb/in	Tests done on samples with a coating weight of 12 lb/ream, prepared under the following extrusion coating conditions: Output Rate: 3 lb/hr/in, Melt Temp: 600°F, Die Width: 12 in, Substrate: 40 lb Kraft paper; ASTM D517

Processing Properties	Metric	English	Comments
Melt Temperature	315 - 325 °C	599 - 617 °F	Optimum adhesion is obtained at a draw span of about 10 cm. Treatment of the substrate or the use of primers will significantly enhance adhesion.

## **Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**