

NOVA Chemicals Novapol® PF-0118-C Butene LLDPE Film Resin

Category : Polymer , Film , Thermoplastic , Polyethylene (PE) , LLDPE , Linear Low Density Polyethylene (LLDPE)/Butene, Film

Material Notes:

Film Properties. Features: Toughness and strength.Applications: Industrial liners, heavy duty bags.Data provided by the manufacturer.

Order this product through the following link:

http://www.lookpolymers.com/polymer_NOVA-Chemicals-Novapol-PF-0118-C-Butene-LLDPE-Film-Resin.php

Physical Properties	Metric	English	Comments
Density	0.918 g/cc	0.0332 lb/in ³	ASTM D792
Thickness	38.1 microns	1.50 mil	
Melt Flow	1.0 g/10 min @Load 2.16 kg, Temperature 190 °C	1.0 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Film Tensile Strength at Yield, MD	11.0 MPa	1600 psi	ASTM D882
Film Tensile Strength at Yield, TD	10.0 MPa	1450 psi	ASTM D882
Film Elongation at Break, MD	600 %	600 %	ASTM D882
Film Elongation at Break, TD	760 %	760 %	ASTM D882
Secant Modulus, MD	0.180 GPa	26.1 ksi	ASTM D882
Secant Modulus, TD	0.200 GPa	29.0 ksi	ASTM D882
Coefficient of Friction	>= 0.40	>= 0.40	ASTM D1894
Elmendorf Tear Strength, MD	3.90 g/micron	99.1 g/mil	ASTM D1922
Elmendorf Tear Strength, TD	11.8 g/micron	300 g/mil	ASTM D1922
Dart Drop	3.70 g/micron	94.0 g/mil	F 50; ASTM D1709/A
Film Tensile Strength at Break, MD	34.0 MPa	4930 psi	ASTM D882
Film Tensile Strength at Break, TD	26.0 MPa	3770 psi	ASTM D882

Optical Properties	Metric	English	Comments
Haze	15 % @Thickness 0.0250 mm	15 % @Thickness 0.000984 in	ASTM D1003

Gloss Optical Properties	45 % Metric	45 % English	45°- 1 mil: ASTM D1894 Comments
Processing Properties			
Melt Temperature	195 - 205 °C	383 - 401 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China