

NOVA Chemicals Sclair® 11M1 Butene LLDPE Film Resin (discontinued **)

Category : Polymer , Film , Thermoplastic , Polyethylene (PE) , LLDPE , Linear Low Density Polyethylene (LLDPE)/Butene, Film

Material Notes:

Film Properties. Features: Low gel, strength and toughness.Applications: Co-extrusion.Data provided by the manufacturer.

Order this product through the following link:

http://www.lookpolymers.com/polymer_NOVA-Chemicals-Sclair-11M1-Butene-LLDPE-Film-Resin-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	0.920 g/cc	0.0332 lb/in ³	ASTM D792
Melt Flow	0.57 g/10 min @Load 2.16 kg, Temperature 190 °C	0.57 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Film Tensile Strength at Yield, MD	10.0 MPa	1450 psi	ASTM D882
Film Tensile Strength at Yield, TD	10.0 MPa	1450 psi	ASTM D882
Film Elongation at Break, MD	600 %	600 %	ASTM D882
Film Elongation at Break, TD	830 %	830 %	ASTM D882
Secant Modulus, MD	0.200 GPa	29.0 ksi	ASTM D882
Secant Modulus, TD	0.220 GPa	31.9 ksi	ASTM D882
Coefficient of Friction	>= 0.50	>= 0.50	ASTM D1894
Elmendorf Tear Strength, MD	7.00 g/micron	178 g/mil	ASTM D1922
Elmendorf Tear Strength, TD	16.0 g/micron	406 g/mil	ASTM D1922
Dart Drop	5.00 g/micron	127 g/mil	F 50; ASTM D1709/A
Film Tensile Strength at Break, MD	35.0 MPa	5080 psi	ASTM D882
Film Tensile Strength at Break, TD	32.0 MPa	4640 psi	ASTM D882

Thermal Properties	Metric	English	Comments
Vicat Softening Point	98.0 °C	208 °F	ASTM D1525
Brittleness Temperature	<= -90.0 °C	<= -130 °F	ASTM D696

Optical Properties	Metric	English	Comments
--------------------	--------	---------	----------

Optical Properties	8.0 % Metric	8.0 % English	Comments ASTM D1003
	@Thickness 0.0250 mm	@Thickness 0.000984 in	
Gloss	55 %	55 %	45°; 1 mil; ASTM D1894

Processing Properties	Metric	English	Comments
Melt Temperature	210 - 220 °C	410 - 428 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China