

NOVA Chemicals Sclair® 11P4 Butene LLDPE Film Resin (discontinued **)

Category : Polymer , Film , Thermoplastic , Polyethylene (PE) , LLDPE , Linear Low Density Polyethylene (LLDPE)/Butene, Film

Material Notes:

Film Properties. Features: Low gel, excellent sealing characteristics, easy processability. Applications: Specialty lamination, co-extrusion. Data provided by the manufacturer.

Order this product through the following link:

http://www.lookpolymers.com/polymer_NOVA-Chemicals-Sclair-11P4-Butene-LLDPE-Film-Resin-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	0.920 g/cc	0.0332 lb/in ³	ASTM D792
Melt Flow	0.72 g/10 min @Load 2.16 kg, Temperature 190 °C	0.72 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Film Tensile Strength at Yield, MD	11.0 MPa	1600 psi	ASTM D882
Film Tensile Strength at Yield, TD	11.0 MPa	1600 psi	ASTM D882
Film Elongation at Break, MD	800 %	800 %	ASTM D882
Film Elongation at Break, TD	800 %	800 %	ASTM D882
Secant Modulus, MD	0.210 GPa	30.5 ksi	ASTM D882
Secant Modulus, TD	0.230 GPa	33.4 ksi	ASTM D882
Coefficient of Friction	0.20	0.20	ASTM D1894
Elmendorf Tear Strength, MD	2.00 g/micron	50.8 g/mil	ASTM D1922
Elmendorf Tear Strength, TD	20.0 g/micron	508 g/mil	ASTM D1922
Dart Drop	3.00 g/micron	76.2 g/mil	F 50; ASTM D1709/A
Film Tensile Strength at Break, MD	42.0 MPa	6090 psi	ASTM D882
Film Tensile Strength at Break, TD	31.0 MPa	4500 psi	ASTM D882

Thermal Properties	Metric	English	Comments
Vicat Softening Point	98.0 °C	208 °F	ASTM D1525
Brittleness Temperature	<= -60.0 °C	<= -76.0 °F	ASTM D696

Optical Properties	Metric	English	Comments
Haze	6.0 % @Thickness 0.0250 mm	6.0 % @Thickness 0.000984 in	ASTM D1003
Gloss	65 %	65 %	45°; 1 mil; ASTM D1894

Processing Properties	Metric	English	Comments
Melt Temperature	220 - 230 °C	428 - 446 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China