

NOVA Chemicals Sclair® 35BPM MDPE Extrusion Resin, 2.2% Carbon Black Filled (discontinued **)

Category : Polymer , Thermoplastic , Polyethylene (PE) , MDPE , Medium Density Polyethylene (MDPE), Extruded

Material Notes:

Features: Excellent ESCR, medium molecular weight, good processability, excellent long term thermal stability, good chemical resistance, excellent UV stability. Applications: Extrusion on to metal pipe to produce a corrosion resistant coating for buried pipe systems. Data provided by the manufacturer.

Order this product through the following link:

http://www.lookpolymers.com/polymer_NOVA-Chemicals-Sclair-35BPM-MDPE-Extrusion-Resin-22-Carbon-Black-Filled-nbspdiscontinued.php

Physical Properties	Metric	English	Comments
Density	0.939 g/cc	0.0339 lb/in ³	Base Density
Water Absorption	0.010 %	0.010 %	ASTM D570
Environmental Stress Crack Resistance	1000 hour	1000 hour	
Melt Flow	0.32 g/10 min @Load 2.16 kg, Temperature 190 °C	0.32 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	60	60	ASTM D2240
Tensile Strength, Ultimate	26.0 MPa	3770 psi	ASTM D638
Tensile Strength, Yield	18.0 MPa	2610 psi	ASTM D638
Elongation at Break	800 %	800 %	ASTM D638
Flexural Modulus	0.590 GPa	85.6 ksi	ASTM D790

Thermal Properties	Metric	English	Comments
Melting Point	128 °C	262 °F	ASTM D3417
Vicat Softening Point	120 °C	248 °F	ASTM D1525
Brittleness Temperature	<= -100 °C	<= -148 °F	ASTM D696

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China