

NOVA Chemicals Sclair® 8405 BK, 8405GBK MDPE Rotational Molding Resin (discontinued **)

Category : Polymer , Thermoplastic , Polyethylene (PE) , MDPE , Medium Density Polyethylene (MDPE), Rotational Molded

Material Notes:

Features: Good ESCR, high impact strength.Applications: Spray tanks.Data provided by the manufacturer.

Order this product through the following link:

http://www.lookpolymers.com/polymer_NOVA-Chemicals-Sclair-8405-BK-8405GBK-MDPE-Rotational-Molding-Resin-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	0.945 g/cc	0.0341 lb/in ³	ASTM D792
Environmental Stress Crack Resistance	250 hour	250 hour	F50, Condition A, ASTM D1693, 100% Igepal
Melt Flow	2.6 g/10 min @Load 2.16 kg, Temperature 190 °C	2.6 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	58	58	ASTM D2240
Tensile Strength, Yield	18.0 MPa	2610 psi	ASTM D638
Elongation at Break	>= 1000 %	>= 1000 %	ASTM D638
Flexural Modulus	0.655 GPa	95.0 ksi	ASTM D790

Thermal Properties	Metric	English	Comments
Vicat Softening Point	114 °C	237 °F	ASTM D1525

Processing Properties	Metric	English	Comments
Melt Temperature	170 - 215 °C	338 - 419 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China