

NOVA Chemicals Surpass® HPs900-C Octene sLLDPE Film Resin

Category : Polymer , Film , Thermoplastic , Polyethylene (PE) , LLDPE , Linear Low Density Polyethylene (LLDPE), Film Grade

Material Notes:

Features: Easy processability Exceptional clarity and gloss Low gel Excellent seal properties Applications: High clarity applications

Lamination film Coextruded sealant layer High toughness film Information provided by Nova Chemicals

Order this product through the following link:

http://www.lookpolymers.com/polymer_NOVA-Chemicals-Surpass-HPs900-C-Octene-sLLDPE-Film-Resin.php

Physical Properties	Metric	English	Comments
Density	0.917 g/cc	0.0331 lb/in ³	ASTM D792
Thickness	25.0 microns	0.984 mil	
Melt Flow	1.0 g/10 min @Load 2.16 kg, Temperature 190 °C	1.0 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Film Tensile Strength at Yield, MD	9.03 MPa	1310 psi	ASTM D882
Film Tensile Strength at Yield, TD	9.03 MPa	1310 psi	ASTM D882
Film Elongation at Yield, MD	520 %	520 %	ASTM D638
Film Elongation at Yield, TD	750 %	750 %	ASTM D882
Puncture Energy	2.10 J	1.55 ft-lb	Low Friction Puncture
Elmendorf Tear Strength MD	280 g	280 g	ASTM D1922
Elmendorf Tear Strength TD	445 g	445 g	ASTM D1922
Dart Drop Test	>= 800 g	>= 1.76 lb	ASTM D1709/A
Film Tensile Strength at Break, MD	49.0 MPa	7110 psi	ASTM D882
Film Tensile Strength at Break, TD	43.0 MPa	6240 psi	ASTM D882
1% Secant Modulus, MD	135.0 MPa	19580 psi	ASTM D882
1% Secant Modulus, TD	155.0 MPa	22480 psi	ASTM D882
Heat Seal Strength Initiation Temperature	100 °C	212 °F	2N

Optical Properties	Metric	English	Comments
Haze	4.0 %	4.0 %	ASTM D1003

Optical Properties	Metric	English	Comments
			at 45 °, ASTM D2457

Processing Properties	Metric	English	Comments
Melt Temperature	185 - 200 °C	365 - 392 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China