

Nabaltec APYMAG® 30S Magnesium Hydroxide

Category : Ceramic , Oxide , Aluminum Oxide , Other Engineering Material , Additive/Filler for Polymer

Material Notes:

The demand for halogen free flame retardant plastics for applications in automobile, electrical, and construction industries is stronger than ever. The use of mineral flame retardants within these products is of growing importance. If processing temperatures exceed 200°C, APYMAG® should be used. It is preferable for applications which are very sensitive to processing parameters, like viscosity. When using in thermoplastics, good mechanical and flame retardancy can be achieved. Information provided by Nabaltec.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Nabaltec-APYMAG-30S-Magnesium-Hydroxide.php

Physical Properties	Metric	English	Comments
Bulk Density	0.600 g/cc	0.0217 lb/in ³	
Density	2.40 g/cc	0.0867 lb/in ³	
Brightness	90 % @Wavelength 457 nm	90 % @Wavelength 457 nm	Whiteness; Elrepho
Oil Absorption	19 %	19 %	(ml/100 g)
Moisture Absorption at Equilibrium	0.50 %	0.50 %	
Loss On Ignition	31 %	31 %	
Particle Size	12 µm	12 µm	Median; Laser Diffraction

Electrical Properties	Metric	English	Comments
Electrical Resistivity	2857 ohm-cm	2857 ohm-cm	

Processing Properties	Metric	English	Comments
Processing Temperature	<= 300 °C	<= 572 °F	

Descriptive Properties	Value	Comments
Magnesium Hydroxide (%)	90	
Sieve Analysis	0.2%	> 45 µm
Stearic Acid (%)	0.5	

Contact Songhan Plastic Technology Co.,Ltd.Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China