

## Nabaltec APYRAL® 8 Al(OH)3

Category : Ceramic , Oxide , Aluminum Oxide , Other Engineering Material , Additive/Filler for Polymer

### Material Notes:

APYRAL ® from Nabaltec is an environmentally friendly halogen free product which is used as a flame retardant filler in a wide variety of rubber and polymeric materials. During thermal decomposition APYRAL ® does not generate toxic or corrosive gases. In addition, there is a distinct reduction in smoke density. APYRAL ® is effective in the crucial phase of the burning process before the outbreak of a fully developed fire. APYRAL ® can be used as a flame retardant filler in ThermosetsElastomersThermoplasticsCable CompoundsTechnical Rubber CompoundsPressed and cast Plastic PartsThermal Insulation FoamsGlass-fiber reinforced plastics

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Nabaltec-APYRAL-8-AIOH3.php](http://www.lookpolymers.com/polymer_Nabaltec-APYRAL-8-AIOH3.php)

Physical Properties	Metric	English	Comments
Bulk Density	0.750 g/cc	0.0271 lb/in <sup>3</sup>	
Density	2.40 g/cc	0.0867 lb/in <sup>3</sup>	
Brightness	92 % @Wavelength 457 nm	92 % @Wavelength 457 nm	Whiteness; Elrepho
Oil Absorption	24 %	24 %	ml/100 g
Moisture Absorption at Equilibrium	0.10 %	0.10 %	
Loss On Ignition	34.6 % @Temperature 105 - 1000 °C	34.6 % @Temperature 221 - 1830 °F	
Particle Size	15 µm	15 µm	Median Grain Diameter
Specific Surface Area	1.3 m <sup>2</sup> /g	1.3 m <sup>2</sup> /g	BET

Mechanical Properties	Metric	English	Comments
Hardness, Mohs	3	3	

Optical Properties	Metric	English	Comments
Refractive Index	1.58	1.58	

Component Elements Properties	Metric	English	Comments
Fe2O3	0.010 %	0.010 %	
Na2O	0.20 %	0.20 %	
SiO2	0.010 %	0.010 %	

Component Elements Properties	Metric	English	Comments
Electrical Properties	Metric	English	Comments
Electrical Resistivity	25000 ohm-cm	25000 ohm-cm	

Descriptive Properties	Value	Comments
Al(OH)3 wt %	99.7	
Crystal Structure	Gibbsite	
Sieve Analysis (%)	3	> 45 µm

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China