

## Nabaltec NABALOX® NO 201 Calcined Aluminum Oxide

Category : Ceramic , Oxide , Aluminum Oxide

**Material Notes:**

NABALOX® aluminum oxide has a number of advantages including low sintering temperaturewide sintering rangeflexible processinghigh sintered densities high wear and impact resistanceelectrical insulationhigh mechanical strengthhigh temperature propertiesdimensional accuracyoptimized chemical resistanceChemical industry, Glass industry, Corundum, Refractory industry, Household ceramics, Electroceramics, Engineering ceramics

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Nabaltec-NABALOX-NO-201-Calcined-Aluminum-Oxide.php](http://www.lookpolymers.com/polymer_Nabaltec-NABALOX-NO-201-Calcined-Aluminum-Oxide.php)

Physical Properties	Metric	English	Comments
Bulk Density	0.800 - 1.00 g/cc	0.0289 - 0.0361 lb/in <sup>3</sup>	
Density	3.60 g/cc	0.130 lb/in <sup>3</sup>	
Loss On Ignition	<= 2.50 % @Temperature 20.0 - 1100 °C	<= 2.50 % @Temperature 68.0 - 2010 °F	
Particle Size	<= 45 µm	<= 45 µm	Less than 20%
Specific Surface Area	50 - 70 m <sup>2</sup> /g	50 - 70 m <sup>2</sup> /g	BET

Component Elements Properties	Metric	English	Comments
Al <sub>2</sub> O <sub>3</sub>	>= 99.5 %	>= 99.5 %	
Fe <sub>2</sub> O <sub>3</sub>	0.030 %	0.030 %	
Na <sub>2</sub> O	0.30 %	0.30 %	
SiO <sub>2</sub>	0.020 %	0.020 %	

Descriptive Properties	Value	Comments
alpha-Al <sub>2</sub> O <sub>3</sub> -Content %	10	
Angle of Response °	35	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China