

Nabaltec NABALOX® NO 615-30 Reactive Alumina

Category : Ceramic , Oxide , Aluminum Oxide

Material Notes:

NABALOX® aluminum oxide has a number of advantages including low sintering temperaturewide sintering rangeflexible processinghigh sintered densities high wear and impact resistanceelectrical insulationhigh mechanical strengthhigh temperature propertiesdimensional accuracyoptimized chemical resistanceRefractory Industry, Engineering Ceramics

Order this product through the following link:

http://www.lookpolymers.com/polymer_Nabaltec-NABALOX-NO-615-30-Reactive-Alumina.php

Physical Properties	Metric	English	Comments
Bulk Density	1.00 - 1.20 g/cc	0.0361 - 0.0434 lb/in ³	
Density	2.70 g/cc	0.0975 lb/in ³	Green Density
	3.87 g/cc	0.140 lb/in ³	Sintered Density
	3.90 g/cc	0.141 lb/in ³	
Loss On Ignition	<= 0.300 % @Temperature 20.0 - 1100 °C	<= 0.300 % @Temperature 68.0 - 2010 °F	
Particle Size	>= 1.5 µm	>= 1.5 µm	Primary Crystal Size
	1.0 - 2.0 µm	1.0 - 2.0 µm	
Specific Surface Area	4.0 - 7.0 m ² /g	4.0 - 7.0 m ² /g	BET

Thermal Properties	Metric	English	Comments
Shrinkage	13 %	13 %	Sintering Shrinkage

Component Elements Properties	Metric	English	Comments
Al ₂ O ₃	>= 99.6 %	>= 99.6 %	
Fe ₂ O ₃	0.030 %	0.030 %	
Na ₂ O	0.30 %	0.30 %	
SiO ₂	0.050 %	0.050 %	

Processing Properties	Metric	English	Comments
Sintering Temperature	1725 °C	3137 °F	

Descriptive Properties	Value	Comments
alpha-Al2O3-Content %	96	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China