

## Nanocyl PLASTICYL™ PA1501 Polyamide 66 with 2 wt% Multi-Wall Carbon Nanotubes

Category : Polymer , Thermoplastic , Nylon , Nylon 66

### Material Notes:

PLASTICYL™ is a family of Multi-Wall Carbon Nanotube (MWNT) thermoplastic concentrates for applications requiring superior electrical conductivity and electrostatic discharge (ESD) properties. PLASTICYL™ PA1501 is a conductive masterbatch based on polyamide 66. Because of its flow formulation, PLASTICYL™ PA1501 is ideal for standard injection molding and extrusion processes. Applications: ESD (Electrostatic Discharge) and electrically conductive parts E&E, automotive, industrial Injection molding, extrusion Benefits: Electrical conductivity at low loading Retention of key mechanical properties Easier processing

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Nanocyl-PLASTICYL-PA1501-Polyamide-66-with-2-wt-Multi-Wall-Carbon-Nanotubes.php](http://www.lookpolymers.com/polymer_Nanocyl-PLASTICYL-PA1501-Polyamide-66-with-2-wt-Multi-Wall-Carbon-Nanotubes.php)

Physical Properties	Metric	English	Comments
Filler Content	2 %	2 %	Carbon Nanotube Loading
Melt Flow	29.18 g/10 min @Load 1.20 kg, Temperature 300 °C	29.18 g/10 min @Load 2.65 lb, Temperature 572 °F	ISO 1133:1997

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	71.88 MPa	10430 psi	ISO 527-1,2
Elongation at Break	2.56 %	2.56 %	ISO 527-1,2
Tensile Modulus	3.205 GPa	464.9 ksi	ISO 527-1,2
Charpy Impact, Notched	0.500 J/cm <sup>2</sup>	2.38 ft-lb/in <sup>2</sup>	ISO 180

Thermal Properties	Metric	English	Comments
Melting Point	263 °C	505 °F	Masterbatch; ISO 11357-1,-3

Electrical Properties	Metric	English	Comments
Volume Resistivity	6.78e+8 ohm-cm	6.78e+8 ohm-cm	CTM E043

Processing Properties	Metric	English	Comments
Processing Temperature	300 °C	572 °F	Material Temperature
Hold Pressure	25.0 MPa	3630 psi	
Back Pressure	0.000 MPa	0.000 psi	

Descriptive Properties	Value	Comments
Processing: Holding Time	25 s	
Processing: Injection Speed	70 cm <sup>3</sup> /s	
Processing: Plasticizing Speed	0.4 m/s	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China