

Network Polymers MS 300 Styrene Methyl Methacrylate Copolymer

Category : Polymer , Thermoplastic , Acrylic (PMMA) , Polystyrene (PS) , Styrene/Methyl Methacrylate Copolymer (SMMA)

Material Notes:

Description: Styrene Methyl Methacrylate Copolymer Information provided by Network Polymers Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Network-Polymers-MS-300-Styrene-Methyl-Methacrylate-Copolymer.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.09 g/cc	1.09 g/cc	ASTM D792
Water Absorption	0.15 %	0.15 %	24 hours; ASTM D570
Linear Mold Shrinkage	0.0020 - 0.0060 cm/cm	0.0020 - 0.0060 in/in	ASTM D955
Melt Flow	2.4 g/10 min @Load 5.00 kg, Temperature 200 °C	2.4 g/10 min @Load 11.0 lb, Temperature 392 °F	Procedure A Condition G; ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	76 - 80	76 - 80	ASTM D785
Tensile Strength, Yield	63.4 MPa	9200 psi	2 in per min; ASTM D638
Elongation at Break	3.0 %	3.0 %	chs 2 in/min; ASTM D638
Flexural Modulus	3.03 GPa	440 ksi	ASTM D638
Izod Impact, Notched	0.214 J/cm	0.400 ft-lb/in	0.125 inch bar; ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	97.8 °C	208 °F	ASTM D648

Optical Properties	Metric	English	Comments
Transmission, Visible	92 %	92 %	ASTM D1003

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China