

Network Polymers NPP 20-1001 C/AS

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Molded

Material Notes:

Description: Random Copolymer Polypropylene, Clarified, with AntistatInformation provided by Network Polymers Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Network-Polymers-NPP-20-1001-CAS.php

Physical Properties	Metric	English	Comments
Density	0.900 g/cc	0.0325 lb/in ³	ASTM D792
Melt Flow	12 g/10 min @Load 2.16 kg, Temperature 230 °C	12 g/10 min @Load 4.76 lb, Temperature 446 °F	Procedure A Condition L; ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	26.2 MPa	3800 psi	2 in per min, tangent; ASTM D638
Elongation at Yield	9.0 %	9.0 %	chs 2 in/min; ASTM D638
Flexural Modulus	0.965 GPa	140 ksi	Test Method I, Procedure B (chs speed 0.05 in/min), Tangent; ASTM D790
Izod Impact, Notched	0.641 J/cm	1.20 ft-lb/in	Test Method A (0.125 in bar); ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	85.0 °C	185 °F	ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China