

Network Polymers PC-1011 L

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate, Molded

Material Notes:

Description: Natural Polycarbonate Information provided by Network Polymers Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Network-Polymers-PC-1011-L.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.20 g/cc	1.20 g/cc	ASTM D792
Water Absorption	0.15 %	0.15 %	24 hours at 73°F; ASTM D570
Linear Mold Shrinkage	0.0040 - 0.0070 cm/cm	0.0040 - 0.0070 in/in	ASTM D955
Melt Flow	10 g/10 min @Load 2.16 kg, Temperature 230 °C	10 g/10 min @Load 4.76 lb, Temperature 446 °F	Procedure A Condition L; ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	120	120	ASTM D785
Tensile Strength, Yield	71.0 MPa	10300 psi	chs 2 in/min; ASTM D638
Flexural Strength	96.5 MPa	14000 psi	Test Method I, Procedure B (chs speed 0.05 in/min); ASTM D790
Flexural Modulus	2.41 GPa	350 ksi	Test Method I, Procedure B (chs speed 0.05 in/min); ASTM D790
Izod Impact, Notched	9.08 J/cm	17.0 ft-lb/in	Test Method A (0.125 in bar); ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	127 °C	260 °F	0.125 in bar; ASTM D648
Flammability, UL94	V-2	V-2	0.062 in, All Colors

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China