

Network Polymers SAN 278 Medium Blue Tint

Category : Polymer , Thermoplastic , SAN Polymer , Styrene Acrylonitrile (SAN), Transparent

Material Notes:

Description: SAN - Styrene Acrylonitrile Transparent Engineering Thermoplastic Information provided by Network Polymers Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Network-Polymers-SAN-278-Medium-Blue-Tint.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.08 g/cc	1.08 g/cc	ASTM D792
Linear Mold Shrinkage	0.0030 - 0.0070 cm/cm	0.0030 - 0.0070 in/in	ASTM D955
Melt Flow	2.0 g/10 min	2.0 g/10 min	Procedure A Condition G; ASTM D1238
	@Load 5.00 kg, Temperature 200 °C	@Load 11.0 lb, Temperature 392 °F	
	7.5 g/10 min	7.5 g/10 min	Procedure A Condition I; ASTM D1238
	@Load 3.80 kg, Temperature 230 °C	@Load 8.38 lb, Temperature 446 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	123	123	ASTM D785
Tensile Strength, Yield	71.7 MPa	10400 psi	chs 2 in/min; ASTM D638
Flexural Modulus	3.63 GPa	526 ksi	Tangent, chs 0.05 in/min; ASTM D790
Izod Impact, Notched	0.214 J/cm	0.400 ft-lb/in	0.125 inch bar; ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	88.9 °C	192 °F	Unannealed/Conditioned 48 hours at 23°C; ASTM D648
Vicat Softening Point	101 °C	214 °F	0.125 inch bar, 1 Kg; ASTM D1525
Flammability, UL94	HB	HB	0.0625 in

Optical Properties	Metric	English	Comments
Haze	1.9 %	1.9 %	ASTM D1003
Transmission, Visible	89 %	89 %	ASTM D1003

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China