

Network Polymers Softflex® 0350

Category : Polymer , Thermoplastic , Elastomer, TPE , Thermoplastic Elastomer, Melt-Processible Rubber

Material Notes:

Description: Softflex® Thermoplastic Elastomer Alloy Information provided by Network Polymers Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Network-Polymers-Softflex-0350.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.910 g/cc	0.910 g/cc	ASTM D792
Linear Mold Shrinkage, Flow	0.017 cm/cm	0.017 in/in	ASTM D955
	@Thickness 3.17 mm	@Thickness 0.125 in	
Linear Mold Shrinkage, Transverse	0.015 cm/cm	0.015 in/in	ASTM D955
	@Thickness 3.17 mm	@Thickness 0.125 in	
Melt Flow	45.5 g/10 min	45.5 g/10 min	Procedure A Condition Q; ASTM D1238
	@Load 1.00 kg, Temperature 235 °C	@Load 2.20 lb, Temperature 455 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	30 - 40	30 - 40	10 second dwell; ASTM D2240
	34 - 44	34 - 44	Instantaneous; ASTM D2240
Tensile Strength, Yield	4.00 MPa	580 psi	chs 20 in/min; ASTM D412
Elongation at Break	950 %	950 %	ASTM D412
Gardner Impact	>= 36.2 J	>= 26.7 ft-lb	ASTM D5420
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Tear Strength	22.8 kN/m	130 pli	ASTM D624

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China