

## **NextGen Adhesives M907-19 Medical Grade Epoxy Adhesive**

Category: Polymer, Adhesive, Thermoset, Epoxy, Epoxy Adhesive

## **Material Notes:**

Description: NGAC M907-19 is a medium viscosity and thixotropic adhesive system that is specifically formulated for medical device assembly applications. Advantages and Applications: Uses include laminating, bonding and sealing applications in the assembly of catheters, hearing aids and dental products, as well as, food preparation and processing equipment. The NGAC M907-19 is easily mixed and cured at room temperature and provides excellent adhesion to glass, ceramic, metal and plastic. Information Provided by Nextgen Adhesives

## Order this product through the following link:

http://www.lookpolymers.com/polymer\_NextGen-Adhesives-M907-19-Medical-Grade-Epoxy-Adhesive.php

| Physical Properties | Metric    | English   | Comments |
|---------------------|-----------|-----------|----------|
| Specific Gravity    | 1.12 g/cc | 1.12 g/cc |          |
| Solids Content      | 100 %     | 100 %     |          |
| Viscosity           | 25000 cP  | 25000 cP  |          |

| Mechanical Properties | Metric   | English  | Comments |
|-----------------------|----------|----------|----------|
| Hardness, Shore D     | 80       | 80       |          |
| Shear Strength        | 13.8 MPa | 2000 psi |          |

| Thermal Properties               | Metric   | English | Comments |
|----------------------------------|----------|---------|----------|
| Maximum Service Temperature, Air | 135 °C   | 275 °F  |          |
| Minimum Service Temperature, Air | -75.0 °C | -103 °F |          |

| Processing Properties | Metric               | English              | Comments |
|-----------------------|----------------------|----------------------|----------|
| Cure Time             | 60.0 - 240 min       | 1.00 - 4.00 hour     |          |
| Cure Time             | @Temperature 65.0 °C | @Temperature 149 °F  |          |
|                       | 1440 min             | 24.0 hour            |          |
|                       | @Temperature 25.0 °C | @Temperature 77.0 °F |          |
| Pot Life              | 45 min               | 45 min               |          |

| Descriptive Properties    | Value   | Comments |
|---------------------------|---------|----------|
| Color                     | Amber   |          |
| Mix Ratio by Weight (R/H) | 108/100 |          |



## **Contact Songhan Plastic Technology Co.,Ltd.**

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China