

## Niche Polymer PA66GF13BK Nylon 66, 13% Glass Fiber Filled

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 10% Glass Fiber Filled

**Material Notes:**

Information provided by Niche Polymer

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Niche-Polymer-PA66GF13BK-Nylon-66-13-Glass-Fiber-Filled.php](http://www.lookpolymers.com/polymer_Niche-Polymer-PA66GF13BK-Nylon-66-13-Glass-Fiber-Filled.php)

Physical Properties	Metric	English	Comments
Linear Mold Shrinkage	0.0550 cm/cm	0.0550 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	107 MPa	15500 psi	ASTM D638
Elongation at Break	3.50 %	3.50 %	ASTM D638
Flexural Strength	172 MPa	24900 psi	ASTM D790
Flexural Modulus	4.83 GPa	700 ksi	ASTM D790
Izod Impact, Unnotched	0.481 J/cm @Thickness 3.17 mm	0.900 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	227 °C	440 °F	ASTM D648

Processing Properties	Metric	English	Comments
Melt Temperature	154 °C	309 °F	ASTM D789

Descriptive Properties	Value	Comments
Color	Black	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China