

Niche Polymer PA66GF43N Nylon 66, 43% Glass Fiber Filled

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 40% Glass Fiber Filled

Material Notes:

Information provided by Niche Polymer

Order this product through the following link:

http://www.lookpolymers.com/polymer_Niche-Polymer-PA66GF43N-Nylon-66-43-Glass-Fiber-Filled.php

Physical Properties	Metric	English	Comments
Linear Mold Shrinkage	0.0250 cm/cm	0.0250 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	221 MPa	32100 psi	ASTM D638
Elongation at Break	3.50 %	3.50 %	ASTM D638
Flexural Strength	290 MPa	42100 psi	ASTM D790
Flexural Modulus	11.0 GPa	1600 ksi	ASTM D790
Izod Impact, Unnotched	1.23 J/cm @Thickness 3.17 mm	2.30 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	249 °C	480 °F	ASTM D648

Processing Properties	Metric	English	Comments
Melt Temperature	254 - 266 °C	489 - 511 °F	ASTM D789

Descriptive Properties	Value	Comments
Color	Natural	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China