

Niche Polymer PA66MI40N Nylon 66, 40% Mineral Fiber Filled, Impact Modified

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, Glass/Mineral Filled , Nylon 66, Impact Grade

Material Notes:

Information provided by Niche Polymer

Order this product through the following link:

http://www.lookpolymers.com/polymer_Niche-Polymer-PA66MI40N-Nylon-66-40-Mineral-Fiber-Filled-Impact-Modified.php

Physical Properties	Metric	English	Comments
Linear Mold Shrinkage	0.00900 cm/cm	0.00900 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	101 MPa	14600 psi	ASTM D638
Elongation at Break	6.00 %	6.00 %	ASTM D638
Flexural Modulus	4.50 GPa	653 ksi	ASTM D790
Izod Impact, Unnotched	1.07 J/cm @Thickness 3.17 mm	2.00 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	75.0 °C	167 °F	ASTM D648

Processing Properties	Metric	English	Comments
Melt Temperature	249 - 260 °C	480 - 500 °F	ASTM D789

Descriptive Properties	Value	Comments
Color	Natural	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China