

Niche Polymer PPCG30BK Copolymer PP, 30% Glass Fiber Filled

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene Copolymer , Polypropylene with 20% Glass Fiber Filler

Material Notes:

Information provided by Niche Polymer

Order this product through the following link:

http://www.lookpolymers.com/polymer_Niche-Polymer-PPCG30BK-Copolymer-PP-30-Glass-Fiber-Filled.php

Physical Properties	Metric	English	Comments
Linear Mold Shrinkage	0.00400 cm/cm	0.00400 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	75.8 MPa	11000 psi	ASTM D638
Elongation at Break	5.00 - 9.00 %	5.00 - 9.00 %	ASTM D638
Flexural Strength	103 MPa	15000 psi	ASTM D790
Flexural Modulus	4.48 GPa	650 ksi	ASTM D790
Izod Impact, Unnotched	1.17 J/cm @Thickness 3.17 mm	2.20 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	146 °C	294 °F	ASTM D648

Processing Properties	Metric	English	Comments
Melt Temperature	149 - 171 °C	300 - 340 °F	ASTM D789

Descriptive Properties	Value	Comments
Color	Black	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China