

Niche Polymer PPHG40BK Homopolymer PP, 40% Glass Fiber Filled

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 20% Glass Fiber Filler

Material Notes:

Information provided by Niche Polymer

Order this product through the following link:

http://www.lookpolymers.com/polymer_Niche-Polymer-PPHG40BK-Homopolymer-PP-40-Glass-Fiber-Filled.php

Physical Properties	Metric	English	Comments
Linear Mold Shrinkage	0.00300 cm/cm	0.00300 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	96.5 MPa	14000 psi	ASTM D638
Elongation at Break	2.50 %	2.50 %	ASTM D638
Flexural Strength	148 MPa	21500 psi	ASTM D790
Flexural Modulus	6.76 GPa	980 ksi	ASTM D790
Izod Impact, Unnotched	1.12 J/cm @Thickness 3.17 mm	2.10 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	157 °C	314 °F	ASTM D648

Processing Properties	Metric	English	Comments
Melt Temperature	171 - 193 °C	340 - 379 °F	ASTM D789

Descriptive Properties	Value	Comments
Color	Black	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China