

Nihon Superior LF-C2 Lead-Free Solder Alloy

Category : Metal , Nonferrous Metal , Solder/Braze Alloy , Tin Alloy

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_Nihon-Superior-LF-C2-Lead-Free-Solder-Alloy.php

Thermal Properties	Metric	English	Comments
Melting Point	208 - 213 °C	406 - 415 °F	
Solidus	208 °C	406 °F	
Liquidus	213 °C	415 °F	

Component Elements Properties	Metric	English	Comments
Bismuth, Bi	3.0 %	3.0 %	
Copper, Cu	1.0 %	1.0 %	
Silver, Ag	3.5 %	3.5 %	
Tin, Sn	92.5 %	92.5 %	As Remainder

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China