

## Nilit FRIANYL A63 HH Nylon 6.6 for injection molding

Category : Polymer , Thermoplastic , Nylon , Nylon 66

### Material Notes:

Nylon 6.6 for injection molding, heat and hydrolysis stabilized Information provided by Frisetta Polymer, which merged into Nilit Plastics

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Nilit-FRIANYL-A63-HH-Nylon-66-for-injection-molding.php](http://www.lookpolymers.com/polymer_Nilit-FRIANYL-A63-HH-Nylon-66-for-injection-molding.php)

Physical Properties	Metric	English	Comments
Density	1.13 g/cc	0.0408 lb/in <sup>3</sup>	ISO 1183
Water Absorption	2.5 - 3.0 %	2.5 - 3.0 %	ISO 62
Water Absorption at Saturation	8.0 - 9.0 %	8.0 - 9.0 %	ISO 62
Viscosity Measurement	145	145	Viscosity index; ISO 307
Linear Mold Shrinkage	0.014 - 0.024 cm/cm	0.014 - 0.024 in/in	FRISSETTA Test Method

Mechanical Properties	Metric	English	Comments
Ball Indentation Hardness	145 MPa	21000 psi	ISO 2039-1
Tensile Strength at Break	90.0 MPa	13100 psi	ISO 527
Elongation at Break	15 %	15 %	ISO 527
Tensile Modulus	3.20 GPa	464 ksi	ISO 527
Flexural Strength	75.0 MPa	10900 psi	ISO 178
Flexural Modulus	2.70 GPa	392 ksi	ISO 178
Charpy Impact Unnotched	NB	NB	ISO 179/1eU
	NB	NB	DIN 53453
	NB	NB	ISO 179/1eU
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	NB	NB	DIN 53453
	NB	NB	DIN 53453
	NB	NB	ISO 179/1eA
	@Temperature -40.0 °C	@Temperature -40.0 °F	
Charpy Impact, Notched	0.500 J/cm <sup>2</sup>	2.38 ft-lb/in <sup>2</sup>	ISO 179/1eA
	0.500 J/cm <sup>2</sup>	2.38 ft-lb/in <sup>2</sup>	DIN 53453
	0.700 J/cm <sup>2</sup>	3.33 ft-lb/in <sup>2</sup>	ISO 179/1eA
	@Temperature -30.0 °C	@Temperature -22.0 °F	

Mechanical Properties	Metric	English	Comments
Melting Point	256 °C	493 °F	ISO 3146 DSC
Maximum Service Temperature, Air	130 °C	266 °F	Continuous; FRISETTA Test Method
Deflection Temperature at 0.46 MPa (66 psi)	200 °C	392 °F	ISO 75
Deflection Temperature at 1.8 MPa (264 psi)	100 °C	212 °F	ISO 75

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	IEC 93
Dissipation Factor	0.020 @Frequency 1e+6 Hz	0.020 @Frequency 1e+6 Hz	IEC 250
Comparative Tracking Index	575 V	575 V	CTI-M 100; IEC 112
	600 V	600 V	CTI 100; IEC 112

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China