

Nilit FRIANYL A63 W-GV15 Nylon 6.6 for injection molding, 15% glass fiber reinforced

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 20% Glass Fiber Filled

Material Notes:

Nylon 6.6 for injection molding, heat stabilized. Information provided by Frisetta Polymer, which merged into Nilit Plastics

Order this product through the following link:

http://www.lookpolymers.com/polymer_Nilit-FRIANYL-A63-W-GV15-Nylon-66-for-injection-molding-15-glass-fiber-reinforced.php

Physical Properties	Metric	English	Comments
Density	1.23 g/cc	0.0444 lb/in ³	ISO 1183
Water Absorption	1.5 - 2.2 %	1.5 - 2.2 %	ISO 62
Water Absorption at Saturation	6.0 - 8.0 %	6.0 - 8.0 %	ISO 62
Viscosity Measurement	145	145	Viscosity index; ISO 307
Linear Mold Shrinkage	0.0050 - 0.022 cm/cm	0.0050 - 0.022 in/in	FRISSETTA Test Method

Mechanical Properties	Metric	English	Comments
Ball Indentation Hardness	170 MPa	24700 psi	ISO 2039-1
Tensile Strength at Break	140 MPa	20300 psi	ISO 527
Elongation at Break	5.0 %	5.0 %	ISO 527
Tensile Modulus	6.00 GPa	870 ksi	ISO 527
Flexural Strength	170 MPa	24700 psi	ISO 178
Flexural Modulus	5.60 GPa	812 ksi	ISO 178
Charpy Impact Unnotched	3.00 J/cm ²	14.3 ft-lb/in ²	DIN 53453
	2.50 J/cm ²	11.9 ft-lb/in ²	DIN 53453
	@Temperature -40.0 °C	@Temperature -40.0 °F	
Charpy Impact, Notched	0.600 J/cm ²	2.86 ft-lb/in ²	DIN 53453

Thermal Properties	Metric	English	Comments
Melting Point	256 °C	493 °F	ISO 3146 DSC
Maximum Service Temperature, Air	115 °C	239 °F	Continuous; FRISSETTA Test Method
Deflection Temperature at 0.46 MPa (66 psi)	250 °C	482 °F	ISO 75

Thermal Properties	Metric	English	Comments
Flammability, UL94	HB	HB	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	IEC 93
Dissipation Factor	0.020 @Frequency 1e+6 Hz	0.020 @Frequency 1e+6 Hz	IEC 250
Comparative Tracking Index	550 V	550 V	CTI 100; IEC 112

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China