

Nilit FRIANYL B63 H-GV25 Nylon 6 for injection molding, 25% glass fiber reinforced

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6, 30% Glass Fiber Filled

Material Notes:

Nylon 6 for injection molding, heat stabilized (dark natural color).Information provided by Frisetta Polymer, which merged into Nilit Plastics

Order this product through the following link:

http://www.lookpolymers.com/polymer_Nilit-FRIANYL-B63-H-GV25-Nylon-6-for-injection-molding-25-glass-fiber-reinforced.php

Physical Properties	Metric	English	Comments
Density	1.31 g/cc	0.0473 lb/in ³	ISO 1183
Water Absorption	1.3 - 2.3 %	1.3 - 2.3 %	ISO 62
Water Absorption at Saturation	6.0 - 8.0 %	6.0 - 8.0 %	ISO 62
Viscosity Measurement	145	145	Viscosity index; ISO 307
Linear Mold Shrinkage	0.0060 - 0.013 cm/cm	0.0060 - 0.013 in/in	FRISSETTA Test Method

Mechanical Properties	Metric	English	Comments
Ball Indentation Hardness	160 MPa	23200 psi	ISO 2039-1
Tensile Strength at Break	160 MPa	23200 psi	ISO 527
Elongation at Break	4.0 %	4.0 %	ISO 527
Tensile Modulus	8.00 GPa	1160 ksi	ISO 527
Flexural Strength	200 MPa	29000 psi	ISO 178
Flexural Modulus	7.30 GPa	1060 ksi	ISO 178
Charpy Impact Unnotched	5.00 J/cm ²	23.8 ft-lb/in ²	DIN 53453
	4.50 J/cm ² @Temperature -40.0 °C	21.4 ft-lb/in ² @Temperature -40.0 °F	DIN 53453
Charpy Impact, Notched	1.50 J/cm ²	7.14 ft-lb/in ²	DIN 53453

Thermal Properties	Metric	English	Comments
Melting Point	221 °C	430 °F	ISO 3146 DSC
Maximum Service Temperature, Air	115 °C	239 °F	Continuous; FRISSETTA Test Method
Deflection Temperature at 0.46 MPa (66 psi)	220 °C	428 °F	ISO 75

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (204 psi)			
Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	IEC 93
Dissipation Factor	0.020 @Frequency 1e+6 Hz	0.020 @Frequency 1e+6 Hz	IEC 250
Comparative Tracking Index	575 V	575 V	CTI 100; IEC 112

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China