

## Nilit FRIANYL B63 HS-GV 5 Nylon 6 for injection molding, 5% glass fiber reinforced

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6, 10% Glass Fiber Filled

### Material Notes:

Nylon 6 for injection molding, high impact modified. Information provided by Frisetta Polymer, which merged into Nilit Plastics

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Nilit-FRIANYL-B63-HS-GV-5-Nylon-6-for-injection-molding-5-glass-fiber-reinforced.php](http://www.lookpolymers.com/polymer_Nilit-FRIANYL-B63-HS-GV-5-Nylon-6-for-injection-molding-5-glass-fiber-reinforced.php)

Physical Properties	Metric	English	Comments
Density	1.15 g/cc	0.0415 lb/in <sup>3</sup>	ISO 1183
Water Absorption	2.0 - 3.0 %	2.0 - 3.0 %	ISO 62
Water Absorption at Saturation	7.0 - 8.0 %	7.0 - 8.0 %	ISO 62
Viscosity Measurement	145	145	Viscosity index; ISO 307
Linear Mold Shrinkage	0.011 - 0.020 cm/cm	0.011 - 0.020 in/in	FRISSETTA Test Method

Mechanical Properties	Metric	English	Comments
Ball Indentation Hardness	95.0 MPa	13800 psi	ISO 2039-1
Tensile Strength at Break	61.0 MPa	8850 psi	ISO 527
Elongation at Break	15 %	15 %	ISO 527
Tensile Modulus	2.80 GPa	406 ksi	ISO 527
Flexural Strength	68.0 MPa	9860 psi	ISO 178
Flexural Modulus	2.10 GPa	305 ksi	ISO 178
Charpy Impact Unnotched	6.20 J/cm <sup>2</sup>	29.5 ft-lb/in <sup>2</sup>	DIN 53453
	NB	NB	ISO 179/1eU
	7.00 J/cm <sup>2</sup>	33.3 ft-lb/in <sup>2</sup>	DIN 53453
	@Temperature -40.0 °C	@Temperature -40.0 °F	
	NB	NB	ISO 179/1eU
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	1.40 J/cm <sup>2</sup>	6.66 ft-lb/in <sup>2</sup>	ISO 179/1eA
	1.40 J/cm <sup>2</sup>	6.66 ft-lb/in <sup>2</sup>	DIN 53453
	1.20 J/cm <sup>2</sup>	5.71 ft-lb/in <sup>2</sup>	DIN 53453

Mechanical Properties	Metric @ Temperature -40.0 °C	English @ Temperature -40.0 °F	Comments
-----------------------	----------------------------------	-----------------------------------	----------

Thermal Properties	Metric	English	Comments
Melting Point	221 °C	430 °F	ISO 3146 DSC
Maximum Service Temperature, Air	100 °C	212 °F	Continuous; FRISETTA Test Method
Deflection Temperature at 0.46 MPa (66 psi)	200 °C	392 °F	ISO 75
Deflection Temperature at 1.8 MPa (264 psi)	160 °C	320 °F	ISO 75

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	IEC 93
Dissipation Factor	0.020 @Frequency 1e+6 Hz	0.020 @Frequency 1e+6 Hz	IEC 250
Comparative Tracking Index	550 V	550 V	CTI 100; IEC 112

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China