

## Nilit FRIANYL B63 KF30 Nylon 6 for injection molding, 30% short glass fiber reinforced

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6, 30% Glass Fiber Filled

### Material Notes:

Nylon 6 for injection molding. Information provided by Frisetta Polymer, which merged into Nilit Plastics

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Nilit-FRIANYL-B63-KF30-Nylon-6-for-injection-molding-30-short-glass-fiber-reinforced.php](http://www.lookpolymers.com/polymer_Nilit-FRIANYL-B63-KF30-Nylon-6-for-injection-molding-30-short-glass-fiber-reinforced.php)

Physical Properties	Metric	English	Comments
Density	1.35 g/cc	0.0488 lb/in <sup>3</sup>	ISO 1183
Water Absorption	1.5 - 2.5 %	1.5 - 2.5 %	ISO 62
Water Absorption at Saturation	7.0 - 8.0 %	7.0 - 8.0 %	ISO 62
Viscosity Measurement	145	145	Viscosity index; ISO 307
Linear Mold Shrinkage	0.0050 - 0.015 cm/cm	0.0050 - 0.015 in/in	FRISSETTA Test Method

Mechanical Properties	Metric	English	Comments
Ball Indentation Hardness	174 MPa	25200 psi	ISO 2039-1
Tensile Strength at Break	90.0 MPa	13100 psi	ISO 527
Elongation at Break	5.0 %	5.0 %	ISO 527
Tensile Modulus	8.00 GPa	1160 ksi	ISO 527
Flexural Strength	110 MPa	16000 psi	ISO 178
Flexural Modulus	7.10 GPa	1030 ksi	ISO 178
Charpy Impact Unnotched	2.50 J/cm <sup>2</sup>	11.9 ft-lb/in <sup>2</sup>	DIN 53453
	2.30 J/cm <sup>2</sup> @Temperature -40.0 °C	10.9 ft-lb/in <sup>2</sup> @Temperature -40.0 °F	DIN 53453
Charpy Impact, Notched	0.600 J/cm <sup>2</sup>	2.86 ft-lb/in <sup>2</sup>	DIN 53453

Thermal Properties	Metric	English	Comments
Melting Point	221 °C	430 °F	ISO 3146 DSC
Maximum Service Temperature, Air	110 °C	230 °F	Continuous; FRISSETTA Test Method
Deflection Temperature at 0.46 MPa (66 psi)	220 °C	428 °F	ISO 75

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (204 psi)			
Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	IEC 93
Dissipation Factor	0.020 @Frequency 1e+6 Hz	0.020 @Frequency 1e+6 Hz	IEC 250
Comparative Tracking Index	575 V	575 V	CTI 100; IEC 112

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China