

Nilit FRIANYL B63 KG20 Nylon 6 for injection molding, 20% chalk filled

Category : Polymer , Thermoplastic , Nylon , Nylon 6

Material Notes:

Nylon 6 for injection molding. Information provided by Frisetta Polymer, which merged into Nilit Plastics

Order this product through the following link:

http://www.lookpolymers.com/polymer_Nilit-FRIANYL-B63-KG20-Nylon-6-for-injection-molding-20-chalk-filled.php

Physical Properties	Metric	English	Comments
Density	1.26 g/cc	0.0455 lb/in ³	ISO 1183
Water Absorption	1.5 - 2.5 %	1.5 - 2.5 %	ISO 62
Water Absorption at Saturation	6.0 - 7.0 %	6.0 - 7.0 %	ISO 62
Viscosity Measurement	145	145	Viscosity index; ISO 307
Linear Mold Shrinkage	0.0080 - 0.019 cm/cm	0.0080 - 0.019 in/in	FRISSETTA Test Method

Mechanical Properties	Metric	English	Comments
Ball Indentation Hardness	140 MPa	20300 psi	ISO 2039-1
Tensile Strength at Break	65.0 MPa	9430 psi	ISO 527
Elongation at Break	16 %	16 %	ISO 527
Tensile Modulus	3.45 GPa	500 ksi	ISO 527
Flexural Strength	50.0 MPa	7250 psi	ISO 178
Flexural Modulus	3.20 GPa	464 ksi	ISO 178
Charpy Impact Unnotched	NB	NB	DIN 53453
	NB	NB	DIN 53453
	@Temperature -40.0 °C	@Temperature -40.0 °F	
Charpy Impact, Notched	0.600 J/cm ²	2.86 ft-lb/in ²	DIN 53453

Thermal Properties	Metric	English	Comments
Melting Point	221 °C	430 °F	ISO 3146 DSC
Maximum Service Temperature, Air	100 °C	212 °F	Continuous; FRISSETTA Test Method
Deflection Temperature at 0.46 MPa (66 psi)	160 °C	320 °F	ISO 75
Deflection Temperature at 1.8 MPa	140 °C	284 °F	

<small>(264 psi)</small> Thermal Properties	Metric	English	ISO 75 Comments
Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	IEC 93
Dissipation Factor	0.020 @Frequency 1e+6 Hz	0.020 @Frequency 1e+6 Hz	IEC 250
Comparative Tracking Index	450 V	450 V	CTI 100; IEC 112

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China