

Nilit FRIANYL B63 SG-GV 2010 Nylon 6 for injection molding, 20% mineral filled and 10% glass fiber reinforced

Category : Polymer , Thermoplastic , Nylon , Nylon 6

Material Notes:

Nylon 6 for injection molding. Information provided by Frisetta Polymer, which merged into Nilit Plastics

Order this product through the following link:

http://www.lookpolymers.com/polymer_Nilit-FRIANYL-B63-SG-GV-2010-Nylon-6-for-injection-molding-20-mineral-filled-and-10-glass-fiber-reinforced.php

Physical Properties	Metric	English	Comments
Density	1.36 g/cc	0.0491 lb/in ³	ISO 1183
Water Absorption	1.0 - 2.0 %	1.0 - 2.0 %	ISO 62
Water Absorption at Saturation	6.0 - 7.0 %	6.0 - 7.0 %	ISO 62
Viscosity Measurement	145	145	Viscosity index; ISO 307
Linear Mold Shrinkage	0.0090 - 0.019 cm/cm	0.0090 - 0.019 in/in	FRISSETTA Test Method

Mechanical Properties	Metric	English	Comments
Ball Indentation Hardness	158 MPa	22900 psi	ISO 2039-1
Tensile Strength at Break	110 MPa	16000 psi	ISO 527
Elongation at Break	3.5 %	3.5 %	ISO 527
Tensile Modulus	6.00 GPa	870 ksi	ISO 527
Flexural Strength	135 MPa	19600 psi	ISO 178
Flexural Modulus	5.00 GPa	725 ksi	ISO 178
Charpy Impact Unnotched	3.00 J/cm ²	14.3 ft-lb/in ²	DIN 53453
	2.70 J/cm ²	12.8 ft-lb/in ²	DIN 53453
	@Temperature -40.0 °C	@Temperature -40.0 °F	
Charpy Impact, Notched	0.600 J/cm ²	2.86 ft-lb/in ²	DIN 53453
	0.700 J/cm ²	3.33 ft-lb/in ²	DIN 53453
	@Temperature -40.0 °C	@Temperature -40.0 °F	

Thermal Properties	Metric	English	Comments
Melting Point	221 °C	430 °F	ISO 3146 DSC

Maximum Service Temperature, Air Thermal Properties	105 °C Metric	221 °F English	Continuous; FRISETTA Test Method Comments
Deflection Temperature at 0.46 MPa (66 psi)	215 °C	419 °F	ISO 75
Deflection Temperature at 1.8 MPa (264 psi)	200 °C	392 °F	ISO 75

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	IEC 93
Dissipation Factor	0.020 @Frequency 1e+6 Hz	0.020 @Frequency 1e+6 Hz	IEC 250
Comparative Tracking Index	400 V	400 V	CTI 100; IEC 112

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China