

Nitriflex PDC-7423 NBR / PVC

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

Material Notes:

Low mold fouling, allowing longer injection runs with reduced mould maintenance and its excellent processability in transfer and injection processes. Indicated for applications that require good resistance to oils and fuels. Contains 15 phr DOP plasticizer. Applications: industrial shoe sole, automotives parts, technical goods. Information provided by Dax Resinas

Order this product through the following link:

http://www.lookpolymers.com/polymer_Nitriflex-PDC-7423-NBR-PVC.php

Physical Properties	Metric	English	Comments
Volatiles	0.00 - 0.70 %	0.00 - 0.70 %	Method B-003; ASTM D5668
Mooney Viscosity	65 - 75 @Temperature 100 °C	65 - 75 @Temperature 212 °F	ML 1+4, Method B-002; ASTM D1646

Descriptive Properties	Value	Comments
Appearance	Light to medium yellow sheets	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China