

Noble Polymers Regis™ 155120 Thermoplastic Olefin (TPO)

Category : Polymer , Thermoplastic , Elastomer, TPE , Olefinic TPE , Thermoplastic Olefinic Elastomer (TPO) , TPO

Material Notes:

Regis is a TPO (thermoplastic olefin) produced by Noble Polymers based on olefin/elastomer compounding. We have created Regis for use in bumpers and bumper fascias, air dams, exterior panels, material handling, step pads and other applications requiring rigid TPOs. This recyclable product is a tough, high-strength thermoplastic that maintains its properties over a wide temperature range. Information provided by Noble Polymers.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Noble-Polymers-Regis-155120-Thermoplastic-Olefin-TPO.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.20 g/cc	1.20 g/cc	ASTM D792
Linear Mold Shrinkage	0.0119 cm/cm	0.0119 in/in	ASTM D955
Melt Flow	5.0 g/10 min @Load 2.16 kg, Temperature 230 °C	5.0 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	11.50 MPa	1668 psi	ASTM D638
Elongation at Break	507.9 %	507.9 %	ASTM D412
Izod Impact, Notched	2.92 J/cm @Temperature -30.0 °C	5.47 ft-lb/in @Temperature -22.0 °F	ASTM D256
	3.99 J/cm @Temperature 23.0 °C	7.47 ft-lb/in @Temperature 73.4 °F	ASTM D256
Gardner Impact	13.6 J @Temperature -30.0 °C	10.0 ft-lb @Temperature -22.0 °F	ASTM D5420
	13.6 J @Temperature 23.0 °C	10.0 ft-lb @Temperature 73.4 °F	ASTM D5420
Tangent Modulus	1050 MPa	153000 psi	ASTM D790

Processing Properties	Metric	English	Comments
Middle Barrel Temperature	191 - 218 °C	375 - 425 °F	
Ejection Temperature	26.7 - 54.4 °C	80.0 - 130 °F	Water Temperature

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China