

# Northstar Polymers MSS-A70GQ High Performance Polyurethane Cast Elastomer System 70A

Category : Polymer , Thermoset , Polyurethane, TS , Thermoset Polyurethane, Liquid

**Material Notes:**

This is a Ester/MDI base high-performance polyurethane casting system. This systems is recommended to applications in which the part requires cut/tear resistance, dry-abrasion resistance, slow response speed, and low energy rebound/response. Ester base systems are generally less expensive than PTMEG base material. Possible applications for this material include skirting for conveyer belts, abrasion resistance liners and parts, and other specialty parts. Unlike conventional full-prepolymer systems, quasi system formulation improves processability, in-mold flow, and components mixing by use of low viscosity prepolymer. This results better physical properties of the products. Can be approved for FDA dry food contact.Information provided by Northstar Polymers.

Order this product through the following link:  
[http://www.lookpolymers.com/polymer\\_Northstar-Polymers-MSS-A70GQ-High-Performance-Polyurethane-Cast-Elastomer-System-70A.php](http://www.lookpolymers.com/polymer_Northstar-Polymers-MSS-A70GQ-High-Performance-Polyurethane-Cast-Elastomer-System-70A.php)

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	70	70	ASTM D2240
Tensile Strength	29.0 MPa	4200 psi	ASTM D412
Elongation at Break	800 %	800 %	ASTM D412
Tear Strength	28.0 kN/m	160 pli	Split; ASTM D624
	52.6 kN/m	300 pli	Die C; ASTM D624
Taber Abrasion, mg/1000 Cycles	12	12	ASTM D4060

Processing Properties	Metric	English	Comments
Processing Temperature	82.2 °C	180 °F	Prepolymer Temperature
	82.2 °C	180 °F	Curing Agent Temperature
Mold Temperature	93.3 °C	200 °F	
Cure Time	15.0 min	0.250 hour	De-mold Time
	@Temperature 93.3 °C	@Temperature 200 °F	
	900 min	15.0 hour	Complete Cure Cycle
	@Temperature 82.2 °C	@Temperature 180 °F	
Pot Life	3.00 min	3.00 min	
Gel Time	4.00 min	4.00 min	

Descriptive Properties	Value	Comments
Curing Agent	SBA-041	
Prepolymer	MSA-018	
Weight Ratio	1:2.219	Prepolymer to Curing Agent Ratio

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China