

## Nyco HARRP™ 20 X 40 Wollastonite

Category : Ceramic , Oxide , Silicon Oxide , Other Engineering Material , Additive/Filler for Polymer

### Material Notes:

HARRP™ 20X40 is suggested for concrete and concrete roof tile reinforcement. Wollastonite is a naturally occurring white mineral with an acicular (needle-shaped) particle structure. This distinctive particle morphology makes wollastonite an ideal performance mineral for a broad range of industrial and consumer applications, including polymer reinforcement; coatings; construction/architecture reinforcement; enhancing friction stability in discs, lings, and brakes; and metallurgy. Information provided by NYCO Minerals.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Nyco-HARRP-20-X-40-Wollastonite.php](http://www.lookpolymers.com/polymer_Nyco-HARRP-20-X-40-Wollastonite.php)

Physical Properties	Metric	English	Comments
Bulk Density	1.40 g/cc	0.0506 lb/in <sup>3</sup>	Loose
	1.55 g/cc	0.0560 lb/in <sup>3</sup>	Tapped
Density	2.90 g/cc	0.105 lb/in <sup>3</sup>	
Solubility in Water	0.0095 %	0.0095 %	
Moisture Absorption	0.0500 %	0.0500 %	
pH	9.9	9.9	10% Slurry
Molecular Weight	116 g/mol	116 g/mol	

Mechanical Properties	Metric	English	Comments
Hardness, Mohs	4.5	4.5	
Tensile Strength	2700 - 4100 MPa	392000 - 595000 psi	Fiber Strength
	@Diameter 0.00300 - 0.150 mm	@Diameter 0.000118 - 0.00591 in	
Modulus of Elasticity	303 - 530 GPa	43900 - 76900 ksi	Fiber Modulus
	@Diameter 0.00300 - 0.150 mm	@Diameter 0.000118 - 0.00591 in	

Thermal Properties	Metric	English	Comments
CTE, linear	6.50 µm/m-°C	3.61 µin/in-°F	
Thermal Conductivity	2.63 - 2.77 W/m-K	18.3 - 19.2 BTU-in/hr-ft <sup>2</sup> -°F	
Melting Point	1410 °C	2570 °F	ASTM D1857
	1540 °C	2800 °F	theoretical

Optical Properties	Metric	English	Comments
Refractive Index	1.63	1.63	

Component Elements Properties	Metric	English	Comments
Al2O3	0.25 %	0.25 %	
CaO	45.72 %	45.72 %	
Fe2O3	0.25 %	0.25 %	
K2O	0.20 %	0.20 %	
Loss on Ignition(%)	6.3 %	6.3 %	
MgO	0.71 %	0.71 %	
MnO	0.020 %	0.020 %	
SiO2	46.52 %	46.52 %	
TiO2	0.050 %	0.050 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	1.30e+13 ohm-cm	1.30e+13 ohm-cm	pure wollastonite
Dielectric Constant	6.8	6.8	
	@Frequency 10000 Hz	@Frequency 10000 Hz	
	6.8	6.8	
	@Frequency 100000 Hz	@Frequency 100000 Hz	
	6.9	6.9	
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
	6.9	6.9	
	@Frequency 1000 Hz	@Frequency 1000 Hz	
Dissipation Factor	0.00152	0.00152	
	@Frequency 1000 Hz	@Frequency 1000 Hz	
	0.0046	0.0046	
	@Frequency 10000 Hz	@Frequency 10000 Hz	
	0.0046	0.0046	
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	

Electrical Properties	Metric	English	Comments
	@Frequency 100000 Hz	@Frequency 100000 Hz	

Descriptive Properties	Value	Comments
Appearance	White	
Bulking Value (gal./lbs.)	0.0413	
Minus 10 U.S. Mesh Screen (%)	100	< 2000 µm
Minus 100 U.S. Mesh Screen (%)	2	< 149 µm
Minus 20 U.S. Mesh Screen (%)	87	< 841 µm
Minus 40 U.S. Mesh Screen (%)	26	< 400 µm
Minus 60 U.S. Mesh Screen (%)	3	< 250 µm
Morphology	Acicular	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China