

Nye Lubricants 140B (SO) Synthetic Oil

Category : Fluid , Lubricant , Synthetic Ether Base , White Mineral Oil (WMO)

Material Notes:

Information provided by Nye Lubricants.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Nye-Lubricants-140B-SO-Synthetic-Oil.php

Physical Properties	Metric	English	Comments
Viscosity Measurement	107	107	Viscosity Index of Base Oil; ASTM D2270
Kinematic Viscosity at 40°C (104°F)	19 cSt	19 cSt	Base Oil; ASTM D445
Kinematic Viscosity at 100°C (212°F)	4.1 cSt	4.1 cSt	Base Oil; ASTM D445
Evaporation Loss	1.80 % @Temperature 121 °C, Time 605000 sec	1.80 % @Temperature 250 °F, Time 168 hour	ASTM D972

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	100 °C	212 °F	Recommended
Minimum Service Temperature, Air	-40.0 °C	-40.0 °F	Recommended
Pour Point	-48.0 °C	-54.4 °F	Base Oil; ASTM D97

Descriptive Properties	Value	Comments
Base Fluid Type	WMO/Ester	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China