

Nye Lubricants 140C (SO) Synthetic Oil

Category : Fluid , Lubricant , Synthetic Ether Base , White Mineral Oil (WMO)

Material Notes:

Information provided by Nye Lubricants.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Nye-Lubricants-140C-SO-Synthetic-Oil.php

| Physical Properties | Metric | English | Comments |
|--------------------------------------|---|---|---|
| Viscosity Measurement | 155 | 155 | Viscosity Index of Base Oil; ASTM D2270 |
| Kinematic Viscosity at 40°C (104°F) | 16 cSt | 16 cSt | Base Oil; ASTM D445 |
| Kinematic Viscosity at 100°C (212°F) | 3.5 cSt | 3.5 cSt | Base Oil; ASTM D445 |
| Evaporation Loss | 2.00 % @Temperature 121 °C, Time 605000 sec | 2.00 % @Temperature 250 °F, Time 168 hour | ASTM D972 |

| Thermal Properties | Metric | English | Comments |
|----------------------------------|----------|----------|--------------------|
| Maximum Service Temperature, Air | 100 °C | 212 °F | Recommended |
| Minimum Service Temperature, Air | -40.0 °C | -40.0 °F | Recommended |
| Pour Point | -48.0 °C | -54.4 °F | Base Oil; ASTM D97 |

| Descriptive Properties | Value | Comments |
|------------------------|-----------|----------|
| Base Fluid Type | WMO/Ester | |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China